

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

Please cancel claims 1-8.

9. (New) A honeycomb structure body comprising:

a plurality of honeycomb segments each having an outer wall, partition walls disposed in the outer wall, and a plurality of cells separated from each other by the partition walls and extending in an axial direction,

a bonding layer interposed between the plurality of honeycomb segments to unitarily bond the honeycomb segments, and

an intermediate layer interposed between the bonding layer and the honeycomb segments;

wherein pores having a diameter of 0.5 μm or more of the intermediate layer occupies 25% by volume or less of the whole volume of the intermediate layer.

10. (New) A honeycomb structure according to Claim 9, wherein the intermediate layer contains 20% by mass of inorganic oxide.

11. (New) A honeycomb structure according to Claim 9, wherein the intermediate layer contains a vitreous phase.

12. (New) A honeycomb structure according to Claim 11, wherein chemical components of the vitreous phase include one or more kinds of alumina, silica, sodium, and potassium.

13. (New) A honeycomb structure body according to Claim 9, wherein predetermined

cells are plugged.

14. (New) A honeycomb structure body according to Claim 9, wherein a catalyst is carried.

15. (New) A method for manufacturing a honeycomb structure body by unitarily bonding, a plurality of honeycomb segments each having an outer wall, partition walls disposed in the outer wall, and a plurality of cells separated from each other by the partition walls and extending in an axial direction,

wherein the method includes a step of disposing an intermediate layer material on the outer walls of the honeycomb segments, a step of disposing a bonding material between the honeycomb segments to unitarily bond the honeycomb segments, and a step of thermally treating the unitarily bonded honeycomb segments at 200 to 1200°C.

16. (New) A method for manufacturing a honeycomb structure body according to Claim 15, wherein an intermediate layer having pores having a diameter of 0.5 μm or more occupying 25% by volume or less of the whole volume of the intermediate layer is formed.

17. (New) A honeycomb structure according to Claim 10, wherein the intermediate layer contains a vitreous phase.

18. (New) A honeycomb structure body according to Claim 10, wherein predetermined cells are plugged.